

2/7/4
DIALOG(R)File 352:Derwent WPI
(c) 2001 Derwent Info Ltd. All rts. reserv.

BEST AVAILABLE COPY

011183345

WPI Acc No: 1997-161270/199715

Prepn. of silica gel with controlled pore volume, etc. - comprises drying
silica hydrogel by batch type fluidised drying method

Patent Assignee: NIPPON SILICA KOGYO KK (NSIL)

Number of Countries: 001 Number of Patents: 001

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
JP 9030809	A	19970204	JP 95185171	A	19950721	199715 B

Priority Applications (No Type Date): JP 95185171 A 19950721

Patent Details:

Patent No	Kind	Lan Pg	Main IPC	Filing Notes
JP 9030809	A	7	C01B-033/158	

Abstract (Basic): JP 9030809 A

Prepn. of silica gel comprises drying silica hydrogel by the batch
type fluidised drying method.

The water content of silica hydrogel is pref. 50-80 wt.%. The batch
type fluidised drying is pref. effected so that the temp. of exhaust
gas is 20-150 de.C. The duration of batch type fluidised drying is
pref. 1-200 mins.. The average particle dia. of hydrogel is pref. 1-20
mm.

ADVANTAGE - The BET specific surface area, pore volume, and average
pore dia. can be controlled and silica gel with sharp pore size
distribution can be produced efficiently.

In an example, a 20 wt.% sodium silicate soln. and a 35 wt.%
sulphuric acid soln. were reacted with a mixing nozzle to obtain silica
hydrosol. The silica hydrosol was gelled in 5 mins. to obtain silica
hydrogel. The silica hydrogel was crushed to a size of 10 mm with a
sieve, treated hydrothermally at 90 deg.C at pH 9.5 for 4 hrs., washed,
and subjected to batch type fluidised drying with the exhaust gas temp.
kept at 61 deg.C.

Dwg.0/5

Derwent Class: E36

International Patent Class (Main): C01B-033/158